

## TECHNICAL SHEET

# ABSO'NET CLASSIC SPECIAL

Industrial Absorbent

### COMPOSITION

Sepiolite

### PHYSICO-CHEMICAL PROPERTIES

	Specifications <sup>1</sup>
<b>Moisture (%)</b>	Max. 12
<b>Bulk density (g/l)</b>	570-670
<b>Water absorption<sup>2</sup> (%)</b>	Min. 135
<b>Gasoil absorption<sup>2</sup> (%)</b>	Min. 85
<b>Particle size distribution by Dry Sieving (%)</b>	
<b>Residue on 1.70 mm</b>	Max. 0.1
<b>Finer than 0.25 mm</b>	Max. 1

<sup>1</sup> Applicable to the whole batch. Uncertainty of the method is not included.

<sup>2</sup> According to standard NF T 90-361.