

## TECHNICAL DATA SHEET

# MINCLEAR H150

### COMPOSITION

Bentonite, acid leached (CAS# 70131-509)

### PHYSICO-CHEMICAL PROPERTIES

	Specifications <sup>1</sup>
Moisture (%)	Max. 15.0
pH	Min. 2.5
Loss on ignition at 1,000°C (%)	Max. 10.0
Free acid (as H <sub>2</sub> SO <sub>4</sub> , %)	Max. 0.4
Particle Size Distribution by Dry Sieving(%) Residue on 150µm	Max. 1.0

<sup>1</sup> Applicable to the whole batch.